

**Amendments to the Claims**

This listing of claims will replace all prior versions, and listings, of claims in the application.

**Listing of Claims**

Claims 1-66. (Canceled)

Claim 67. (Previously Presented) A display element of the information screen or advertising panel type, comprising:

a plurality of juxtaposed electrochemical devices, each comprising at least one substrate (1,7), at least one electroconductive layer (2,6), at least one electrochemically active layer (3,5) that is capable of reversibly inserting ions, and an electrolyte (4), wherein the electrolyte (4) is a layer or a multilayer stack comprising at least one layer (4b) made of an ionically conductive material that is capable of reversibly inserting said ions but whose overall degree of oxidation is maintained essentially constant.

Claim 68. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein said inserted ions are  $H^+$ ,  $Li^+$ ,  $Na^+$ ,  $Ag^+$  or  $K^+$ .

Claim 69. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein the overall degree of oxidation of the layer (4b) of the electrolyte (4) is maintained essentially constant by electrically insulating said layer (4b) from at least one of the electron

sources of the device by interposing at least one layer (4a,4d) of an electronically insulating material.

Claim 70. (Currently Amended) The display element according to Claim 40 69, wherein the layer(s) (4a,4d) made of electronically insulating material is ionically conductive/ion-permeable.

Claim 71. (Currently Amended) The display element according to Claim 41 70, wherein the layer(s) (4a,4d) made of electronically insulating material forms part of the multilayer electrolyte (4) in direct contact with at least one of the faces of the layer (4b) having an overall degree of oxidation maintained essentially constant.

Claim 72. (Currently Amended) The display element according to Claim 38 67, wherein the overall degree of oxidation of the layer (4b) of the electrolyte (4) is maintained essentially constant by keeping the potential of said layer (4b) at values outside the range of potentials causing a variation in the degree of ion insertion of the material of which it is composed.

Claim 73. (Currently Amended) The display element according to Claim 38 67, wherein, in said device, in succession, an electroconductive layer (2), an electrochemically active layer (3) that is capable of reversibly inserting cations, the electrolyte (4) comprising layer (4b) made of ionically conductive material that is capable of reversibly inserting cations

but whose overall degree of oxidation is maintained essentially constant, and optionally at least one electronically insulating layer (4a,4c), a second electrochemically active layer (5) that is capable of reversibly inserting cations, and an electroconductive layer (6).

Claim 74. (Currently Amended) The display element according to Claim [44] 73, wherein said layer (3) is a cathodic electrochromic material and said layer (5) is of an anodic electrochromic material.

Claim 75. (Currently Amended) The display element according to Claim 38 67, wherein the material of layer (4b) that is capable of reversibly inserting the ions but whose degree of oxidation is maintained essentially constant, is a material exhibiting an electrochromic property.

Claim 76. (Currently Amended) The display element according to Claim 38 67, wherein the material exhibiting an electrochromic property of the layer (4b) is maintained in the decolored state or in an intermediate state of coloration.

Claim 77. (Currently Amended) The display element according to Claim 38 67, wherein the electrochemical device operates by reversible insertion of protons from the an electrochemically active layer or layers (3,5) and in that the material of the layer (4b) of the electrolyte (4), which is capable of reversibly inserting protons, but whose degree of oxidation is maintained essentially constant, is based on a metal oxide or a mixture of metal oxides,

optionally hydrated, and selected from the group consisting of tungsten oxide, optionally hydrated,  $\text{WO}_3 \cdot n\text{H}_2\text{O}$ , niobium oxide, optionally hydrated,  $\text{Nb}_2\text{O}_5 \cdot n\text{H}_2\text{O}$ , optionally hydrated,  $\text{NiO}_x \text{H}_y \cdot n\text{H}_2\text{O}$ , tin oxide, optionally hydrated,  $\text{SnO}_2 \cdot n\text{H}_2\text{O}$ , bismuth oxide, optionally hydrated,  $\text{Bi}_2\text{O}_3 \cdot n\text{H}_2\text{O}$ , titanium oxide, optionally hydrated,  $\text{TiO}_2 \cdot n\text{H}_2\text{O}$ , vanadium oxide, optionally hydrated,  $\text{V}_2\text{O}_5 \cdot n\text{H}_2\text{O}$ , molybdenum oxide, optionally hydrated,  $\text{MoO}_3 \cdot n\text{H}_2\text{O}$ , where  $n \geq 0$  and optionally comprising an additive metal, which can be hydrated, of titanium, tantalum, rhenium, or of an alkali metal.

Claim 78. (Currently Amended) The display element according to Claim 38 67, wherein the electrochemical device operates by reversible insertion of lithium ions  $\text{Li}^+$  from the an electrochemically active layer or layers (3,5), the material of said layer (4b) of the electrolyte (4), which is capable of reversibly inserting lithium ions  $\text{Li}^+$ , but whose degree of oxidation is maintained essentially constant, being based on a metal oxide or a mixture of metal oxides, which optionally are lithiated and are selected from the group consisting of nickel oxide  $\text{NiO}_x$ , lithiated nickel oxide  $\text{Li}_y\text{NiO}_x$ , a mixture of titanium and cerium oxides  $\text{CeTiO}_x$ , tungsten oxide  $\text{WO}_3$ , niobium oxide  $\text{Nb}_2\text{O}_5$ , vanadium oxide  $\text{V}_2\text{O}_5$  and lithiated oxide vanadium oxide  $\text{Li}_x\text{V}_2\text{O}_5$ .

Claim 79. (Currently Amended) The display element according to Claim 40 69, wherein the layer or layers (4a,4d) of electronically insulating material comprises at least one oxide of a metal of column VB of the Periodic Table and at least one metal oxide selected from the group consisting of antimony oxide  $\text{Sb}_2\text{O}_5$ , zirconium oxide  $\text{ZrO}_2$ , titanium oxide  $\text{TiO}_2$ ,

silicon oxide  $\text{SiO}_2$ , chromium oxide  $\text{CrO}_3$ , these oxides being optionally hydrated and optionally comprising a hydratable metal additive of W, Re or an alkali metal.

Claim 80. (Currently Amended) The display element according to Claim ~~50~~ 79, wherein said metal oxide is a mixed Ta-Ti oxide,  $\text{GeO}_3$  or  $\text{ZnO}(\text{H}_3\text{PO}_4)_2 \cdot \text{H}_2\text{O}$ .

Claim 81. (Currently Amended) The display element according to Claim ~~40~~ 69, wherein the layers (4a,4c) of electronically insulating material is formed of  $\text{CeF}_3$ , hexa-uranylphosphate HUP,  $\text{MgF}_2$ ,  $\text{CaF}_2$ ,  $\text{SiO}_x$ ,  $\text{LiF}$ ,  $\text{Na}_3\text{AlF}_6$  or based on  $\text{Li}_3\text{N}$ ,  $\text{LiTaO}_3$ ,  $\text{LiAlF}_4$ ,  $\text{Li}_3\text{PO}_4$ ,  $\text{LiPO}_2$ ,  $\text{LiN}$ ,  $\text{LiNbO}_3$ ,  $\text{MgF}_2\text{POLi}$  or  $\text{Li}_2\text{WO}_4$ , said device operating by reversible insertion of lithium ions from the electrochemically active layer or layers (3,5).

Claim 82. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein the materials which form layer (4b) are capable of reversibly inserting the ions but whose degree of oxidation is maintained essentially constant and/or materials forming the layers (4a,4d) made of electronically insulating material are nitrated and/or phosphatized.

Claim 83. (Currently Amended) The display element according to Claim ~~40~~ 69, wherein the layers (4a,4d) made of electronically insulating material is a material whose electrical insulation properties are obtained by blocking its ability to insert ions by controlling its potential.

Claim 84. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein the multilayer electrolyte (4) comprises a layer made of an ionically conductive material (4c) in the form of an aqueous liquid or of an anhydrous liquid or based on polymer(s) or on a gel(s).

Claim 85. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein the electrochemically active layers (3,5) comprise a layer (5) of cathodic electrochromic material selected from the group consisting of and in that the material of the layer (4b) of the electrolyte (4), which is capable of reversibly inserting protons, but whose degree of oxidation is maintained essentially constant, is based on a metal oxide or a mixture of metal oxides, optionally hydrated, and selected from the group consisting of tungsten oxide  $\text{WO}_3$ , molybdenum oxide  $\text{MoO}_3$ , vanadium oxide  $\text{V}_2\text{O}_5$ , niobium oxide  $\text{Nb}_2\text{O}_5$ , titanium oxide  $\text{TiO}_2$  a cermet material of the  $\text{WO}_3/\text{Au}$  or  $\text{WO}_3/\text{Ag}$  type, a mixture of tungsten and rhenium oxides  $\text{WO}_3/\text{ReO}_3$ , and phosphotungstic acid, metallophthalocyanines or metallodibenzophthalocyanines of transition metals or of rare earths, optionally nitrated.

Claim 86. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein the electrochemically active layers comprise a layer (3) of anodic electrochromic material in the form  $\text{M}_x\text{A}_y\text{U}_z$ , where M is a transition metal, A is the ion used for the reversible insertion, and U is a chalcogenide, which is optionally nitrated.

Claim 87. (Currently Amended) The display element according to Claim ~~57~~ 86, wherein the chalcogenide is S, O or Se.

Claim 88. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein the electrochemically active layers comprise a layer (3) of anodic electrochromic material which, in the case of the reversible insertion of protons, is selected from the group consisting of  $\text{LiNiO}_x$ ,  $\text{IrO}_x\text{H}_y$ ,  $\text{IrO}_x\text{H}_y\text{N}_z$ ,  $\text{NiO}_x$ ,  $\text{NiO}_x\text{H}_y$ ,  $\text{NiO}_x\text{H}_y\text{N}_z$ ,  $\text{RhO}_x$ ,  $\text{CoO}_x$ ,  $\text{CrO}_x$ ,  $\text{MnO}_x$ , and a hydride of a rare earth, of a lanthanide or of transition metals and, in the case of reversible insertion of lithium ions  $\text{Li}^+$  selected from the group consisting of  $\text{LiNO}_x$ ,  $\text{LiMn}_2\text{O}_4$ ,  $\text{IrO}_x$ ,  $\text{Li}_x\text{IrO}_y$ ,  $\text{NiO}_x$ ,  $\text{CeO}_x$ ,  $\text{TiO}_x$ ,  $\text{CeO}_x\text{-TiO}_x$ ,  $\text{RhO}_x$ ,  $\text{CoO}_x$ ,  $\text{CrO}_x$ ,  $\text{MnO}_x$ ,  $\text{VO}_x$ ,  $\text{Li}_x\text{CoO}_y$ ,  $\text{LiCrO}_y$ ,  $\text{LiVO}_y$ ,  $\text{ReO}_x$ ,  $\text{RhO}_x$ ,  $\text{PtO}_x$ ,  $\text{FeO}_x$ ,  $\text{OsO}_y$ ,  $\text{CuO}_x$ ,  $\text{PrO}_x$ , these compounds being optionally lithiated and/or nitrated and, in the case of insertion of protons or of  $\text{Li}^+$  or of hexacyanometalates, of formula  $\text{M}[\text{M}'(\text{CN})_6]$ , with M and M' being transition metals and/or rare earths.

Claim 89. (Currently Amended) The display element according to Claim ~~38~~ 67, wherein at least one of the electroconductive layers (2,6) comprises at least one doped metal oxide selected from the group consisting of ITO or  $\text{SnO}_2\text{:F}$ , or a metal or a metal alloy selected from the group consisting of gold, silver, aluminum or Ni-Cr alloy or is the superposition of several layers of these materials.

Claim 90. (Currently Amended) The display element according to Claim 38 67, wherein the multilayer electrolyte (4) and all of the layers of the said device contain only layers of solid material.

Claim 91. (Currently Amended) The display element according to Claim 38 67, wherein the multilayer electrolyte comprises a layer made of an electric insulator in the form of a gel or a polymer.

Claim 92. (Currently Amended) The display element according to Claim 38 67, wherein the multilayer electrolyte is  $(\text{NiO}_x\text{H}_y \cdot n \text{H}_2\text{O}/\text{WO}_3 \cdot n \text{H}_2\text{O})_n$ , with  $n \geq 1$ .

Claim 93. (Currently Amended) The display element according to Claim 38 67, wherein the multilayer electrolyte is  $(\text{NiO}_x\text{H}_y \cdot n \text{H}_2\text{O}/\text{WO}_3 \cdot n \text{H}_2\text{O})_p$  or  $(\text{Ta}_2\text{O}_5 \cdot n \text{H}_2\text{O}/\text{WO}_3 \cdot n \text{H}_2\text{O})_p$  with  $n \geq 2$ .

Claim 94. (Currently Amended) The display element according to Claim 38 67, wherein at least a substrate is a plastic substrate.

Claim 95. (Currently Amended) The display element according to Claim 38 67, wherein at least a substrate is a thin flexible plastic sheet.